PATENT COOPERATION TREATY



PCT

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY (Chapter II of the Patent Cooperation Treaty)

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference 0000054141	FOR FURTHER ACTION	See Form PCT/IPEA/416					
International application No. PCT/EP2003/013743	International filing date (day/month/yea 05 December 2003 (05.12.200)						
International Patent Classification (IPC) or national classification and IPC B41C 1/05							
Applicant BASF DRUCKSYSTEME GMBH							
 This report is the international preliminary examination report, established by this International Preliminary Examining Authority under Article 35 and transmitted to the applicant according to Article 36. 							
2. This REPORT consists of a total of sheets, including this cover sheet.							
3. This report is also accompanied by ANNEXES, comprising:							
a. (sent to the applicant and							
sheets of the description, claims and/or drawings which have been amended and are the basis of this report and/or sheets containing rectifications authorized by this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions).							
sheets which supersede earlier sheets, but which this Authority considers contain an amendment that goes beyond the disclosure in the international application as filed, as indicated in item 4 of Box No. I and the Supplemental Box.							
b. (sent to the International Bureau only) a total of (indicate type and number of electronic carrier(s)) , containing a sequence listing and/or tables related thereto, in computer readable form only, as indicated in the Supplemental Box Relating to Sequence Listing (see Section 802 of the Administrative Instructions).							
4. This report contains indications relating to the following items:							
Box No. I Basis of the re	Box No. I Basis of the report						
Box No. II Priority	Box No. II Priority						
Box No. III Non-establish	Box No. III Non-establishment of opinion with regard to novelty, inventive step and industrial applicability						
Box No. IV Lack of unity	Box No. IV Lack of unity of invention						
Box No. V Reasoned state	Box No. V Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement						
[]							
Box No. VII Certain defects	Box No. VII Certain defects in the international application						
Box No. VIII Certain observ	<u> </u>						
Date of submission of the demand	Date of complet	Date of completion of this report					
05 May 2004 (05.05.2	004)	01 March 2005 (01.03.2005)					
Name and mailing address of the IPEA/EP	Authorized offic	Authorized officer					
Facsimile No.	Telephone No.	Telephone No.					

Translation

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

International application No.

PCT/EP2003/013743

Box No	. 1	Basis of the report						
1. With other	regard wise in	to the language, this report is based on the international application in the land dicated under this item.	guage in which it was filed, unless					
	This report is based on translations from the original language into the following language, which is language of a translation furnished for the purpose of:							
	international search (under Rules 12.3 and 23.1(b))							
		publication of the international application (under Rule 12.4)						
	international preliminary examination (under Rules 55.2 and/or 55.3)							
furni	shed to are not	to the elements of the international application, this report is based on the receiving Office in response to an invitation under Article 14 are referre annexed to this report): tternational application as originally filed/furnished	(replacement sheets which have been ed to in this report as "originally filed"					
		scription:						
	pages	1-21						
1	pages		, as originally filed/furnished					
1	pages							
	the cl pages	aims:	, as originally filed/furnished					
	pages	as amended (tog)	ether with any statement) under Article 19					
	pages	,,	04 September 2004 (04.09.2004)					
	pages		0.120010012001					
	4- 4							
		awings:						
	pages	1/1	, as originally filed/furnished					
İ	pages pages							
	pages	received by this Authority on						
	a sequ	ence listing and/or any related table(s) - see Supplemental Box Relating to Sec	quence Listing.					
3.	The a	nendments have resulted in the cancellation of:						
		the description, pages						
	Ħ	the claims, Nos.						
	the drawings, sheets/figs							
		the sequence listing (specify):						
		any table(s) related to sequence listing (specify):						
4.	made, (Rule	eport has been established as if (some of) the amendments annexed to this resince they have been considered to go beyond the disclosure as filed, as 70.2(c)). the description, pages the claims, Nos the drawings, sheets/figs the sequence listing (specify): any table(s) related to sequence listing (specify):	eport and listed below had not been indicated in the Supplemental Box					
* If item 4 applies, some or all of those sheets may be marked "superseded."								

International application No.
PCT/EP 03/13743

V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement

1.	Statement			
	Novelty (N)	Claims	1-8	YES
		Claims _	9-11	NO
	Inventive step (IS)	Claims	1-8	YES
		Claims	9-11	NO
	Industrial applicability (IA)	Claims	1-11	YES
		Claims		NO

2. Citations and explanations

Reference is made to the following documents:

D1: DE-A-10118987 (BASF Drucksysteme GmbH)

D2: DE-A-10113926 (BASF Drucksysteme GmbH)

Claims 1-8

- 1. The closest prior art is disclosed in DE-A-10113926 (D2). D2 discloses a method for producing flexographic printing forms by laser engraving in which, as a starting material, a photopolymerisible flexographic printing element is used comprising at least the following items arranged one above the other
 - (a) a dimensionally stable support
 - (b) a photopolymerisible, relief-forming layer at least 0.3mm thick, at least comprising an elastomeric bonding agent, an ethylenically unsaturated monomer, and a photo initiator, and
 - (c) a protective element that is substantially permeable to actinic light, said protective element being a film that is treated or coated in an anti-adhesive manner on the side facing

the relief-forming layer,

wherein the method comprises the following steps in this sequence:

- (a') removing the protective layer
- (b') cross-linking the relief-forming layer over the entire volume of the layer by irradiation with actinic light, and
- (c) engraving a printing relief in the cross-linked relief-forming layer using a laser that emits between 3000 and 12000 nm, the depth of the relief elements that are to be engraved with a laser being at least 0.03 mm.

The present method differs from the prior art in that the method comprises the following steps in this sequence:

- (a) cross-linking the relief-forming layer over the entire volume of the layer by irradiating actinic light through the protective element
- (b) removing the protective element, and
- (c) engraving a printing relief in the cross-linked relief-forming layer using a laser that emits between 3000 and 12000 nm, the depth of the relief elements that are to be engraved with the laser being at least 0.03mm,

and the protective element being a film that is treated or coated in an anti-adhesive manner on the side facing the relief-forming layer and that is applied directly to the relief-forming layer, wherein the adhesion between the protective element and the relief-forming layer is set such that the protective element can be removed from the crosslinked, relief-forming layer after method step (a).

The method according to claim 1 is therefore novel.

The present invention addresses the problem of providing a method for producing flexographic printing forms by laser engraving, in which the appearance of melt edges during laser engraving is prevented (see pages 1-3).

This problem solved in that the photopolymerisible, relief-forming layer is protected against hardening by actinic light by means of a protective element that is substantially permeable to actinic light, said protective element consisting of a film that is treated or coated in an anti-adhesive manner on the side facing the relief-forming layer. The adhesion between the protective element and the relief-forming layer is set such that the protective element can be removed from the cross-linked, relief-forming layer after hardening is complete across the entire surface.

The solution to this problem is not apparent from the prior art and is therefore not obvious to a person skilled in the art.

The subject matter of the present claim 1 therefore involves an inventive step.

Claims 9-11

1. Clarity (PCT Article 6)

The present claim 9 defines a photopolymerisible flexographic printing element having a photopolymerisible (that is, unhardened) relief-

forming layer by means of a desired property of the photopolymerised (that is, hardened) layer, namely:

The adhesion between the protective element and the relief-forming layer is set such that the protective element can be removed from the cross-linked relief-forming layer <a href="mailto:after:a

This definition is unclear for two reasons:

- The features are not features of the photopolymerisible flexographic printing element, but of the cross-linked flexographic printing element obtained after a further method step.
- The flexographic printing element is defined via a desired property (the protective element should be able to be removed after hardening), without indicating how this property is to be achieved.

Novelty (PCT Article 33(2))

- Owing to the lack of clarity of the present claim 9 indicated above in point 1 (Guidelines C-III 4.4, C-IV 7.5), any photopolymerisible flexographic printing element which comprises the following items arranged one above the other:
 - (a) a dimensionally stable support
 - (b) a photopolymerisible, relief-forming layer at least 0.3mm thick, at least comprising an elastomeric bonding agent, an ethylenically unsaturated monomer, and a photo initiator, and
 - (c) a protective element that is substantially permeable to actinic light, said protective element being a film that is treated or coated

in an anti-adhesive manner on the side facing the relief-forming layer is covered by the definition given in claim 9.

- 2.2 D1 and D2 disclose photopolymerisible flexographic printing elements comprising the following items arranged one above the other,
 - (a) a dimensionally stable support
 - (b) a photopolymerisible, relief-forming layer at least 0.3 mm thick, at least comprising an elastomeric bonding agent, an ethylenically unsaturated monomer, and a photo initiator, and
 - (c) a protective element that is substantially permeable to actinic light, said protective element being a film that is treated or coated in an anti-adhesive manner on the side facing the relief-forming layer (see D1 and D2, entire documents).

D1 and D2 therefore disclose all the technical features of the present claim 9, insofar as said features are clear.

The subject matter of the present claim 9 is therefore not novel over D1 and D2 and therefore does not meet the requirements of PCT Article 33(2).

2.3 Dependent claims 10 and 11 do not appear to contain any additional features which, in combination with the features of any claim to which claims 10 and 11 refer back, meet the PCT requirements for novelty and inventive step.